

Class:

S1P SRC

Sizes: 38-47

Instep: 12

EN ISO 20345:2011

Weight(±10%): 510 gr. (*)

TECHNICAL SHEET ART. BOWLING

Description Low shoe in nut microfiber with padded storm-cuff, 100% polyester lining, Non-Metallic HRP Insole , SPORT-LITE Insole anatomic antistatic and antibacterical , double density polyurethane sole , bending resistant , abrasion resistant , oil resistant , slip resistant , ESD.

Plus Midsole compound particularly studied to get a soft PU density for a higher comfort

Suggested sectors of usage Building/construction, Utilities, Servicing, Mechanical Industry, Professional / Craftsman, Electronic & Electrotechnic, Logistic/Packaging

Care and Maintenance clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source.



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
Toe Cap : Non-Metallic Thin Cap toe cap, impact resistant 200 J	5.3.2.3	Impact resistance	mm	14,5	≥14
	5.3.2.4	Compression resistance	mm	16,0	≥ 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100 without holes	≥ 1.100
ESD footwear : dissipation capacity of the electrostatic charge	EN ISO	Resistance to floor			
	61340	(footwear/floor resistance)	Ohm	$3,88 \times 10^7$	$<$ 1,00 x $10^{8} \Omega$
	5-1:2016	Transverse resistance of the sole	Ohm	$3,05 \times 10^7$	\leq 1,00 x $10^{8} \Omega$
		Chargeability	V	<20 V	< 100 V
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	24,0	≥ 20
Upper: Nut microfiber	5.4.6	Water vapour permeability	mg/cm ² h	6,3	≥ 0,8
		Coefficient of permeability	mg/cm²	53,7	≥ 15
	5.4.3	Tearing Strength	N	126	≥ 60
Vamp and Quarter Lining : honeycomb finished polyester, breathable, abrasion	5.5.3	Water vapour permeability	mg/cm² h	6,2	≥ 2
resistant, yellow colour		Coefficient of permeability	mg/cm²	52,8	≥ 20
	5.5.1	Tearing Strength	N	73	≥ 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Insole lining: textile anti perforation midsole HRP insole	5.7.3	Water Absorption	mg/cm²	76	≥ 70
		Ability to release water		99%	≥ 80%
Sole : double density polyurethane , bending resistant, abrasion resistant, oil	5.8.2	Tearing Strength	kN/m	8,9	≥ 8
resistant, slip resistant, ESD	5.8.3	Abrasion resistance	mm³	86	≤ 150
	5.8.4	Bending resistance	mm	0,5	≤ 4
	5.8.5	Hydrolysis	mm	1,5	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	0,5%	≤ 12%
	5.11	Slip resistance on ceramic floor with water and	flat	0 ,4 7	≥ 0,32
		detergent	inclined	0,32	≥ 0,28
		Slip resistance on steel floor with glycerine	flat	0,24	≥ 0,18
			inclined	0,22	≥ 0,13

Golf style and its components: no presence of dangerous substances by Annex VII to regulation no. 1907/2006/CE and subsequent amendments and additions $^{(*)}$ = Indicative weight that refers to $\frac{1}{2}$ pair in size 42